

sarbak



TECHNICAL DATA SHEET

CW617N - CuZn40Pb2

S617 - S617DW
RODS / HOLLOW RODS

Product Code	EN Symbol	EN No	ASTM		Cu	Zn	Pb	Sn	Fe	Ni	Al	Si	Others Total
S617	CuZn40Pb2	CW617N	C38000	Min (%)	57,0	Rem.	1,6	-	-	-	-	-	-
				Max (%)	59,0	Rem.	2,5	0,3	0,3	0,3	0,05	-	0,2
(*) S617DW	CuZn40Pb2-DW	CW617N-DW	C38000	Min (%)	57,0	Rem.	1,6	-	-	-	-	-	-
				Max (%)	59,0	Rem.	2,2	0,3	0,3	0,1	0,05	0,03	0,2

(*) Each of the other elements < 0,02 %

Features And Applications

CW617N is mainly used standard hot forging material. It has a good machinability capability due to lead content. Also this alloy compliance with RoHS II and REACH directives. CW617N-DW alloy be used suitable for 4MS vs UBA list for drinking water applications.

4MS and UBA Hygienic list group for CW617N-DW alloy: B, C, D

Area of Usage

Hot forging parts.

TECHNICAL SPECIFICATIONS

Structure	$\alpha+\beta$	Hot Forming	650-800 °C
Machinability	% 95	Soft Annealing	450-600 °C
Density	8,43g/cm ³	Soft Annealing Time	1-3 hours
Electrical Conductivity	14,9 MS/m, 25 %IACS	Stress Relieving	200-300 °C
Thermal Conductivity	113 W/(m·K)	Stress Relieving Time	1-3 hours
Elasticity Module	96 GPa		
Coeff. of Thermal Expansion	21,1 10 ⁻⁶ /K		
Melting Point	880-895 °C		


Range of Products

S617 and S617-DW alloys can be produced in our extrusion and cold drawing unit as rods, hollows and profiles suitable for both forging and machining. Please contact us for other technical informations.

INDICATIVE SHAPED ENDS DIMENSIONS

Nominal Diameter or Width		Type A - Chamfer Length (L)		Type B - Point Length (L)	
Across-flats (mm)		Min (mm)	Max (mm)	Min (mm)	Max (mm)
Over	Up to and including				
5	10	0,2	1,5	2	7
10	20	0,2	2	3	10
20	30	0,2	3	4	12

Unless otherwise specified by the buyer, the shape of the ends of products larger than 30 mm is up to the supplier.



Nominal Diameter or Width Across-flats (mm)		Preferred (available) Lengths (mm)	Tolerance on Length (mm)
Over	Up to and including		
5	30	3.000 - 4.000	±50
30	80	3.000 - 4.000	±100

Stress Relieving The polygonal rods and hollow rods are subjected to stress relieving treatment

Packaging 500 or 1000 kg bundle - 3/5 metal straps different bundle packagings, up to 10 mm dimension products are packed with wooden case

EN 12164 - Rods for Free Machining

Material Condition	Nominal Diameter (mm)		Width Across-flats (mm)		Tensile Strength R _m N/mm ² (MPa) Min	0,2 % Proof Strength N/mm ² (MPa)		Elongation			Hardness (HBW)	
	Over	Up to and inc.	Over	Up to and inc.		Min	Max	A _{100mm} (%) Min	A _{11,3} (%) Min	A (%) Min	Min	Max
M	All		All		As manufactured							
R360	6	80	5	55	360	-	350	-	15	20	-	-
H090	6	80	5	55	-	-	-	-	-	-	90	125
R430	5	60	5	40	430	220	-	6	8	10	-	-
H110	5	60	5	40	-	-	-	-	-	-	110	160
R500	5	14	5	10	500	350	-	-	3	5	-	-
H135	5	14	5	10	-	-	-	-	-	-	135	-

EN 12168 - Hollow Rods for Free Machining

Material Condition	Wall Thickness (mm)		Tensile Strength R _m N/mm ² (MPa) Min	0,2 % Proof Strength N/mm ² (MPa)		Elongation A (%) Min	Hardness (HBW)		Hardness (HV)	
	Over	Up to and inc.		Min	Max		Min	Max	Min	Max
M	All		As manufactured							
R360	3	40	360	-	320	20	-	-	-	-
H090	3	40	-	-	-	-	90	125	100	135
R430	3	15	430	220	-	10	-	-	-	-
H110	3	15	-	-	-	-	110	160	120	170
R500	3	7	500	350	-	8	-	-	-	-
H135	3	7	-	-	-	-	135	-	145	-

EN 12165 - Wrought and Unwrought Forging Stocks

Material Condition	Nominal Diameter (mm)		Hardness (HBW)	
	Over	Up to and including	Min	Max
M	All		As manufactured	
H080	8	80	80	125

STANDARD		EN 12164			EN 12165		EN 12168					
Dimension Range		Round Rod		Hexagonal, Square	Round Rod		Round and Hexagonal Hollow Rod, Outer Dim. Tol.			Hole Tolerance Round		Hole Tol. Hexagonal
Over	Up to & inc.	Class A	Class B	Rod	Class A	Class B	Class A	Class B	Class C	Class A	Class B	-
5	6	0 -0,05	0 -0,03	0 -0,08	-	-	-	-	-	-	-	-
6	10	0 -0,06	0 -0,036	0 -0,09	±0,25	±0,14	-	-	-	-	-	-
10	13	0 -0,07	0 -0,043	0 -0,11	±0,25	±0,14	-	-	-	-	-	-
13	18	0 -0,07	0 -0,043	0 -0,11	±0,25	±0,14	-	-	-	±0,35	-	+0,70 -0
18	20	0 -0,08	0 -0,052	0 -0,13	±0,30	±0,17	-	-	-	±0,42	-	+0,84 -0
20	23	0 -0,08	0 -0,052	0 -0,13	±0,30	±0,17	-	-	-	±0,42	±0,17	+0,84 -0
23	26	0 -0,08	0 -0,052	0 -0,13	±0,30	±0,17	-	0 -0,21	-	±0,42	±0,17	+0,84 -0
26	30	0 -0,08	0 -0,052	0 -0,13	±0,30	±0,17	-	0 -0,21	0 -0,13	±0,42	±0,17	+0,84 -0
30	50	0 -0,16	-	0 -0,16	±0,60	±0,20	-	0 -0,25	0 -0,16	±0,80	±0,20	+1,6 -0
50	55	0 -0,19	-	0 -0,19	±0,70	±0,37	-	0 -0,46	0 -0,30	±0,95	±0,37	-
55	65	0 -0,19	-	-	±0,70	±0,37	±0,60	0 -0,46	0 -0,30	±0,95	-	-
65	80	0 -0,19	-	-	±0,70	±0,37	±0,60	0 -0,46	0 -0,30	±0,95	-	-
80	120	-	-	-	±2	-	-	-	-	-	-	-
120	140	-	-	-	±2,5	-	-	-	-	-	-	-

For Hollow Rods

Minimum wall thickness is 3 mm. Eccentricity : %10 (max.)

Outer Cold Drawn - Internal Extruded
 Outer Class B - Hole Class A tolerance

Inner-Outer Cold Drawn
 Outer Class C - Hole Class B tolerance

Inner-Outer Extruded
 Outer Class A - Hole Class A tolerance



Headquarter

Eđitim Mah. Adım Sok. Orjin İş Merkezi No: 10 -18 Kat: 3 Daire No: 39 - 49 34722
Hasanpaşa / Kadıköy / İstanbul / Turkey
T: +90 216 414 45 35 pbx | F: +90 216 414 45 40

Factory

Çerkezköy Organize Sanayi Bölgesi Gazi Osman Paşa Mah. 8.Cad. No: 3 59500
Çerkezköy / Tekirdađ / Turkey
T: +90 282 725 19 60 pbx | F: +90 282 725 19 70